



INTERIOR ACOUSTICS

FRONTIER™

MANUFACTURERS GUARANTEE

Pat. Pending NZ 727634, AU 2016273959

Frontier™ is manufactured by Autex Industries Ltd and Autex Australia Pty Ltd under an ISO 9001 certified Quality Management System. The product is guaranteed to be free from manufacturing defects and carries a Manufacturer's Guarantee for a period of no less than ten years to meet all of the performance properties stated within this guarantee.

Product Name Frontier™
Description 100% polyester complete modular acoustic fins

EN13501-1:2007+A1:2009

B - s2, d2
 WF 336911 dated 25th February, 2014

ASTM E-84-15a

Class A, FS:0 - SD:45
 RJ4479-2 dated 25th January, 2015

AUTEX	METRIC		IMPERIAL	
Size	Fin Width: 2400mm		7.8'	
	12mm: Pack Covers 5.0m ²		1/2": Pack Covers 54ft ²	
	24mm: Pack Covers 2.5m ²		1": Pack Covers 27ft ²	
Thickness	12mm	24mm	1/2"	1"
Tolerance	(+/- 6%)	(+/- 6%)	(+/- 6%)	(+/- 6%)
Weight	2300gsm	4600gsm	7.54oz/ft ²	15.07oz/ft ²

ACOUSTIC PERFORMANCE

Frontier is specifically designed to reduce and control reverberating noise in building interiors.

Sound Absorption Coefficients according to ISO 354. University of Auckland Testing Service Frontier 12mm - Test No. T1525-1, T1525-16, and T1525-17. Frontier Axis - Test No. T1525-11

Pack Size

Thickness	Fin	Channels	Connectors	Pack Weight
12mm	8	8	16	20kg
12mm (Axis only)	16	8	16	
24mm	4	4	8	

	Frequency (Hz)	125	250	500	1000	2000	4000	NRC
Tundo, Dune, Sierra and Atlas	aP 100mm spacing	0.30	0.65	0.80	1.00	1.00	1.00	1.00
	aP 200mm spacing	0.30	0.60	0.70	1.00	1.00	1.00	0.90
	aP 300mm spacing	0.25	0.50	0.60	0.80	1.00	1.00	0.75
Axis	Frontier Axis	0.20	0.50	0.75	0.65	0.90	1.00	0.70

COMPOSITION

100% Polyester Fibre from polyethylene terephthalate (PET). Made from Autex Cube™ which contains a minimum of 45% previously recycled polyester fibre.

SUITABLE APPLICATIONS

Suspended or direct fix with patented aluminium channels and connector clips.

COLOUR FASTNESS TO LIGHT

Frontier is suitable for indoor use only. Light fastness is dependent on use and exposure. Frontier has been evaluated to the following standard:

ISO 105-B02:2014

Rating: 6 (Highest = 7)

FIRE RATINGS

Frontier™ is a value-added product made from Autex Cube™ acoustic panels as the base material. Cube™ (12mm) has been evaluated using the following test methods:

ISO 9705: 1993

Classification: Group 1-S

Smoke Production Rate: <5.0m²/s

As required by NZBC C/VM2

AS ISO 9705 - 2003

Classification: Group 1

(SMOGR_{arc}): <100m²/s²

Assessed using methodology AS ISO 9705 - 2003 in accordance with AS 5637.1:2015, as required by BCA Specification C1.10-4

Fl 4974 dated 16th September, 2012

VOC EMISSIONS

Autex polyester has been tested for chemical emissions in accordance with ASTM D5116 and is considered as a low VOC product.

VOC concentration: 0.009 mg/m³ (7 days)

FINISH

Non-woven. No pattern repeat but Frontier™ has a directional grain. Product may vary from samples and batch to batch due to fibre blending and lay-up which is an inherent feature of this product.

PHYSICAL DESCRIPTION / PROPERTIES

Boiling Point:	N/A
Melting Point:	250°C 482°F
Vapour Pressure:	N/A
Specific Gravity:	Polyester 1.38
Flash point:	N/A
Explosive limits:	N/A
Solubility in water:	Not soluble
Alkalinity:	pH 7.8
Relative Vapour Density:	N/A

CARE AND MAINTENANCE

Maintain in accordance with the Care and Maintenance Guide available for this product.

